

| REPORT DOCUMENTATION PAGE | | | | Form Approved OMB No. 0704-0188 | |
|---|-----------------------------|-----------------------------------|---------------------------------------|--|--|
| Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS. | | | | | |
| 1. REPORT DATE (DD-MM-YYYY) July 2015 | | 2. REPORT TYPE Briefing Charts | | 3. DATES COVERED (From - To) July 2015-August 2015 | |
| 4. TITLE AND SUBTITLE Isocyanate-Free Elastomers as Replacements for Isocyanate-cured Polyurethanes (Briefing Charts) | | | | 5a. CONTRACT NUMBER In-House | |
| | | | | 5b. GRANT NUMBER | |
| | | | | 5c. PROGRAM ELEMENT NUMBER | |
| 6. AUTHOR(S) Josiah T. Reams, Andrew J. Guenther, Jacob C. Marcischak, Michael D. Ford, Timothy S. Haddad, Gregory R. Yandek, Joseph M. Mabry | | | | 5d. PROJECT NUMBER | |
| | | | | 5e. TASK NUMBER | |
| | | | | 5f. WORK UNIT NUMBER Q0BG | |
| 7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Air Force Research Laboratory (AFMC) AFRL/RQRP 10 E. Saturn Blvd. Edwards AFB, CA 93524-7680 | | | | 8. PERFORMING ORGANIZATION REPORT NO. | |
| 9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Air Force Research Laboratory (AFMC) AFRL/RQR 5 Pollux Drive Edwards AFB CA 93524-7048 | | | | 10. SPONSOR/MONITOR'S ACRONYM(S) | |
| | | | | 11. SPONSOR/MONITOR'S REPORT NUMBER(S) AFRL-RQ-ED-VG-2015-301 | |
| 12. DISTRIBUTION / AVAILABILITY STATEMENT Distribution A: Approved for Public Release; Distribution Unlimited. | | | | | |
| 13. SUPPLEMENTARY NOTES Briefing Charts presented at 250th ACS National Meeting; Boston, MA; 16-20 August 2015. PA#15447. | | | | | |
| 14. ABSTRACT Briefing Charts | | | | | |
| 15. SUBJECT TERMS | | | | | |
| 16. SECURITY CLASSIFICATION OF: | | | 17. LIMITATION OF ABSTRACT SAR | 18. NUMBER OF PAGES 24 | 19a. NAME OF RESPONSIBLE PERSON Joseph Mabry |
| a. REPORT Unclassified | b. ABSTRACT Unclassified | c. THIS PAGE Unclassified | | | 19b. TELEPHONE NO (include area code) 661-275-5857 |



Isocyanate-Free Elastomers as Replacements for Isocyanate-cured Polyurethanes

Josiah T. Reams, Andrew J. Guenther, Jacob C. Marcischak, Michael D. Ford, Timothy S. Haddad, Gregory R. Yandek, Joseph M. Mabry

ACS National meeting
20 August 2015



Josiah Reams, Ph.D.
ERC Inc. / Air Force Research Laboratory
josiah.reams.ctr@us.af.mil
(661) 275-5664

DISTRIBUTION A: Approved for public release; distribution is unlimited. .



Outline



- **Goal**
 - Investigate polymeric cure systems with crosslinking chemistries that are unlikely to pose health concerns now and in the future
- **Objective**
 - Synthesis of new isocyanate-free candidate binder formulations
 - Determine impact physical and mechanical properties
 - Demonstrate the use of new polymeric binders in binder formulation
- **Technical Challenges**
 - Maintain energy content and I_{sp}
 - New system must conform to current binder processing operations
 - Retention of physical and mechanical properties of HTPB / isocyanate systems
 - Low T_g
 - High elongation to break
 - Compatibility with high solids loading
- **Approach**
 - Nucleobase binding
 - Thiolene “click” chemistry

Acknowledgements:

- Strategic Environmental Research and Development Program (SERDP)
- Air Force Office of Scientific Research, Air Force Research Laboratory – Program Support; PWG team members (AFRL/RQRP)






Background: Isocyanates

- Isocyanates are prized for their high reactivity; they are particularly useful for production of energetic materials where high temperatures must be avoided
- Isocyanates are a respiratory irritant and a significant cause of occupational asthma
- Sensitization can occur at very low levels of exposure, with effects continuing for many years afterward
- Cross-sensitization (e.g. dermal exposure leading to sensitization of respiratory tract) has also been reported.
- Isocyanates are not found in nature; their high reactivity without specificity makes them unsuitable for complex biological systems
- Increased regulation will result in increased cost and eventual unavailability in the U.S.






Nucleobase Binding



- DNA is biologically ubiquitous therefore no current environmental regulation and likely no regulation in the future
- Potential advantages
 - Dynamic covalent chemistry is a hot topic
 - Potential for self-healing properties
 - Reversible crosslinks have the potential for easy demilitarization
 - Insensitivity
- Potential risks of nucleobase crosslinked polymer systems
 - Polymers containing nucleobase monomers are rare and therefore are not commercially available
 - Properties not well understood




Incorporation of Nucleotide Bases in Polybutadiene



Copolymerization of either adenine or thymine methacrylate with butadiene gives an “A” and “B” complimentary copolymers

Cheng, S; Zhang, M.; Dixit, N.; Moore, R. B.; Long, T. E. *Macromolecules*, 2012 45, 805-812.




- When in the presence of each other complimentary copolymers associate and form a crosslinked system consisting of hydrogen bonds
- Both components exist as low viscosity liquids and do not self-associate
- When mixed together, the two part system is initially a low viscosity liquid that forms a crosslinked network as complimentary nucleobases associate




Adenine Acrylate Co-Butadiene Polymerization Variability





- Thymine copolymer displays low T_g comparable to polybutadiene homopolymer, however Adenine copolymer self associates
- Variability in Adenine copolymerization was observed with respect to nucleobase incorporation



2.5 mol % adenine incorporation






9.0 mol % adenine incorporation








DNA Nucleobase Polymer Properties




- In polar media adenine units do not self associate, however non-polar media promotes self-association
- Self association of individual “part A” or “part B’ components makes mixing of two components difficult
- Too many unknown characteristics of self- and cross-association for near-term development of reliable cross-linking substitute



Carbon-Sulfur Bonds as Crosslinks




- Many sulfur containing compounds exist in nature including proteins
- Thiol-ene chemistry not biologically ubiquitous like nucleobase binding
- Thiol-ene chemistry similar to free radical in terms of reactivity but with more control and selectivity
- Utilization of existing vinyl double bonds in commercial polybutadiene





Thiol-Ene Chemistry




- Thiol-ene chemistry is a hybrid of free radical and condensation chemistry. It combines the speed and ease of initiation of free radical chemistry with the product specificity of condensation chemistry.
- As a type of “click” chemistry, it generates no volatiles and minimal side products.




Peroxide Catalyzed Thiol-ene Click




Peroxides




Lauroyl Peroxide
Luperox ® LP
64 °C




t-butylperoxy 2-ethylhexyl carbonate,
Luperox ® TBEC
100 °C




t-butyl peroxybenzoate
Luperox ® P
104 °C



Benzoyl Peroxide
73 °C






AIBN



Dicumyl Peroxide
117 °C (DCP)

Thiols




1,9-Nonanedithiol, 95%

- Many available peroxide initiators with different 10 hour half-life temperatures allow reactivity to be tuned to processing conditions
- Ratio of peroxide to thiol can be varied to tune rate of initiation
- Choice of thiol affects crosslink density and hydrolytic stability
- Peroxide-initiated nonanedithiol /HTPB cure was chosen to match current HTPB-isocyanate processing conditions at 60 °C




Thiol-ene Crosslinked HTPB



- HTPB cured with 1,9-nonanedithiol / TBEC (peroxide) at 5:1 SH / O₂, 60 °C, for 8 days under N₂. Data point labels (left figure) indicate fraction of available –SH incorporated into gel, a measure of conversion.
- Glass transition temperatures remain at acceptable levels over a wide range of cure conditions




Importance of Network Architecture



Chain backbone (1,4 addition)

Vinyl groups (1,2 addition)

Hydroxyl end groups





- Free radical polymerized HTPB
 - Mixture of 1,4 and 1,2 addition
 - Hydroxyl end-group functionality 2.4-2.6 / per chain
 - T_g -75 °C
 - Molecular Weight M_n = 2800 g/mol
 - Polydispersity ~2.5









Importance of Network Architecture



Isocyanates react only with end groups, producing few branches and junctions




Thiols react with pendant vinyl groups, producing many junctions and branches




Reproduction of correct polymer architecture is necessary to obtain correct mechanical properties



Thiol-ene cured HTPB Modulus



Luperox® P



Luperox® TBEC

| Peroxide | Thiol | SH:HTPB | Theoretical Modulus (psi) | Measured Modulus* (psi) |
|-----------|-------------|---------|---------------------------|-------------------------|
| Luperox P | 1,9 Dithiol | 3:1 | 215 | 141 |
| Luperox P | 1,9 Dithiol | 4:1 | 360 | 331 |
| TBEC | 1,9 Dithiol | 3:1 | 492 | 419 |
| TBEC | 1,9 Dithiol | 4:1 | 851 | 502 |

* Compressive modulus at 298K measured by thermomechanical analysis (TMA)

- Mechanical property data suggests thiol-ene cured HTPB has a lower molecular weight between crosslinks and isocyanate cured HTPB
- Reaction at chain ends rather than at pendant vinyl groups is necessary to achieve correct architecture and mechanical properties




Strategies for Desirable Architecture



- **HTPB without vinyl side groups**
- **Polybutadiene (PB) with low vinyl incorporation**
 - Polybutadiene with 1% vinyl
 - Difficult to tell the position of vinyl groups on polymer chain
 - Initial investigation with nonanedithiol cure produces elastomeric material
- **Thiol-terminated polyethylene glycol (PEG) system**
 - Co-cured with di and tri-functional vinyl compounds
 - Demonstration of principle in progress
- **Thiol-terminated polybutadiene**
 - Co-cure with di and tri-functional vinyl groups
 - Presence of main chain vinyl groups will result in intramolecular reaction / cyclization
 - Synthesis of polybutadiene with di-anionic initiator to produce cis-1,4 substituted polybutadiene




Thiol-Terminated Polybutadiene (from HTPB)








Thiol-terminated polybutadiene

- Presence of main chain vinyl groups will result in intramolecular reaction / cyclization
- Co-cure with di and tri-functional vinyl groups





Thiol-terminated HTPB Synthesis




- Reaction conditions optimized for hydroxyl protection with mesylate. Side reactions were observed in the presence of triethylamine and methanol
- Trans mesylate groups were surprisingly unreactive
- Formation of thiol terminated HTPB was accompanied by concomitant thiol-ene formation
- Propensity of thiol groups to undergo initiator-free thiolene click chemistry makes use of HTPB backbone impractical for real world use



Thiol Terminated Hydrogenated Polybutadiene Synthesis




HLBH 3000




- Hydroxyl protection with mesylate groups proceeds without formation of side products as occurs with HTPB
- Formation of thiol terminated HLBH 3000 is obtained in good yield with high conversion, i.e. all hydroxyl groups present have equal reactivity
- Reduction of thioacetate to thiol is accompanied by disulfide formation (~25%)


Thioacetate



Mesylate




Thiol Terminated





Vinyl Ether-Terminated Hydrogenated Polybutadiene





Impact of Results on Future DoD Operations



- **Elimination of isocyanates alleviates a major occupational health and safety concern in the manufacture and use of solid rocket motor propellants.**
- **Elimination of isocyanates also mitigates issues related to moisture sensitivity during propellant mixing and casting, and may reduce some forms of degradation during long-term storage in humid environments.**
- **Replacement of isocyanates with chemical groups that are ubiquitous in the biosphere will greatly reduce the risk associated with future regulation / obsolescence throughout the manufacturing, use, and de-militarization life cycle.**
- **Alternative cure chemistries that are successful for solid rocket motors may be transitioned to other applications, such as paints, foams, sealants, and adhesives that also represent a significant source of occupational health risk for DoD and DOE.**



Conclusions

- **Increasing regulation of isocyanates in the workplace poses a significant, but not insurmountable, challenge to DoD/DOE operations**
- **DNA nucleobase technology represents a promising future path to isocyanate replacement, but is not yet mature enough for near-term development in solid rocket motors**
- **Thiol-ene chemistry represents a safer alternative to isocyanate chemistry that remains a promising candidate for near-term development in solid rocket motor propellants**
- **When paired with the proper polymer architecture, thiol-ene based propellants will offer simpler manufacturing, improved quality control, greatly reduced occupational health and safety concerns, and some potential decrease in humid ageing in solid rocket motor propellants.**

QUESTIONS?



U.S. AIR FORCE

DISTRIBUTION A: Approved for public release; distribution is unlimited.